

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 May 2004 (21.05.2004)

PCT

(10) International Publication Number
WO 2004/041847 A1

(51) International Patent Classification⁷: **C07K 1/00**,
G01N 33/68, C30B 29/58, 7/00, B01D 9/02

(21) International Application Number:
PCT/GB2003/004875

(22) International Filing Date:
7 November 2003 (07.11.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0225980.2 7 November 2002 (07.11.2002) GB

(71) Applicant (for all designated States except US): **IMPERIAL COLLEGE INNOVATIONS LIMITED**
[GB/GB]; Sherfield Building, Imperial College, London SW7 2AZ (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **CHAYEN, Naomi**

[GB/GB]; Biological Structure & Function Section, Division of Biomedical Sciences, Sir Alexander Fleming Building, Faculty of Medicine, Imperial College, London SW7 2AZ (GB). **HENCH, Larry** [US/GB]; Centre for Tissue Engineering, Department of Materials, Imperial College of Science, Technology & Medicine, Prince Consort Road, London SW7 2BP (GB).


(74) Agent: **PILKINGTON, Stephanie**; Eric Potter Clarkson, Park View House, 58 The Ropewalk, Nottingham NG1 5DD (GB).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),

[Continued on next page]

(54) Title: MESOPOROUS GLASS AS NUCLEANT FOR MACROMOLECULE CRYSTALLISATION



(57) Abstract: A method of facilitating the crystallisation of a macromolecule comprising the step of adding a mesoporous glass to a crystallisation sample wherein the mesoporous glass comprises pores having diameters between 4nm and 100nm and has a surface area of at least 50 m²/g. A method of facilitating the crystallisation of a macromolecule comprising the step of adding to a crystallisation sample a mesoporous glass of the composition SiO₂; CaO-P₂O₅-SiO₂ or Na₂O-CaO-P₂O₅-SiO₂, wherein each of the Ca, P, Si or Na atoms within the compositions may be substituted with a suitable atom chosen from B, Al, Ti, Mg, or K, and, optionally, the composition may also include heavy elements to enhance X-ray diffraction contrast such as Ag, Au, Cr, Co, Sr, Ba, Pt, Ta or other atom with an atomic number over 20.

WO 2004/041847 A1



Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

— before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.